

### **Technical Data Sheet**

## **Product Description**

DuPont 6179T conductor (20:1:0.3 silver/palladium/platinum) is suitable for low-cost hybrid circuits or resistor networks.

### **Product Benefits**

- Excellent aged adhesion
- Excellent thru-hole printability
- Good Solderability and excellent solder leach resistance.

# Processing Printing


DuPont 6179T prints easily using 325 mesh stainless steel screens with a 12-14 μm emulsion.

### **Drying**

Allow prints to level for 5-10 minutes at room temperature. Then dry for 10-15 minutes at 150° C, in a well ventilated oven or belt dryer.

### **Firing**

Fire in well ventilated moving conveyor furnace, in air with a 30 minute cycle to a peak temperature of 850°C.



# **Typical Physical Properties**

Test	Properties
Resistivity (mΩ/sq) (μm)	≤12 @ 15
Fired Thickness [µm]	10 - 15
Aged Adhesion (N)	>25
Solder Leach Resistance [Number of 10 second dips in 62Sn/36Pb/2Ag Solder per micron of fired thickness]	0.6

# Composition Properties Viscosity (Pa.S) (Brookfield HBT, 10 rpm #14 spindle&UC, 25°C) Thinner DuPont 4553 Shelf Life [months]

This table shows anticipated typical physical properties for DuPont 6179T based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

## Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

### Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont<sup>™</sup>, The miracles of science<sup>™</sup>, Green Tape<sup>™</sup> and all products or words denoted with ® or <sup>™</sup> are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates ("DuPont"). NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 ("Medical Applications Policy") and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user's consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data's accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user's responsibility to satisfy itself that the product is suitable for the user's intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.

For more information on DuPont 6179T or other DuPont Microcircuit

Materials products, please contact your local representative:

### **Americas**

**DuPont Microcircuit Materials** 

14 T.W. Alexander Drive

Research Triangle Park, NC 27709

Tel.: 800-284-3382

### Europe

Du Pont (U.K.) Limited

Coldharbour Lane

Bristol BS16 1QD

U.K

Tel.: 44-117-931-3191

#### <u>Asia</u>

DuPont Kabushiki Kaisha

**DuPont Electronic Center** 

KSP R&D B213, 2-1, Sakado 3-chome, Takatsu-ku,

Kawasaki-shi, Kanagawa, 213-0012, Japan

Tel: +81-44-820-7575

**DuPont Taiwan Ltd** 

45, Hsing-Pont Road,

Taoyuan, Taiwan 330

Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd

Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,

Pudong New District, Shanghai 201203, China

Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.

3~5th Floor, Asia tower #726,

Yeoksam-dong, Gangnam-gu

Seoul 135-719, Korea

Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited

7th Floor, Tower C, DLF Cyber Greens,

Sector-25A, DLF City, Phase-III,

Gurgaon 122 002 Haryana, India

Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd

1 HarbourFront Place, #11-01

HarbourFrong Tower One,

Singapore 098633

Tel.: 65-6586-3022

http://mcm.dupont.com

