

DuPont 9615R

GLASS ENCAPSULANT

Technical Data Sheet

Product Description

High temperature glass encapsulant composition DuPont 9615R intended for use as final encapsulant to provide hermetic protection for screen printed capacitors. DuPont 9615R is applied to ceramic substrate by screen printing and fired in an air (oxidizing) atmosphere.

Product Benefits

- Red color dried film, colorless fired film
- Coefficient of thermal expansion 6.3×10^{-6} in/in/°C (0-300°C)
- Hermetic fired film with excellent chemical durability
- Fired at a peak temperature of 850°C
- Phthalate, cadmium, and nickel oxide free*

*Phthalate, cadmium, and nickel "free" as used herein means that these are not intentionally added to the referenced product. Trace amounts however may be present.

Processing Printing

Encapsulant composition DuPont 9615R should be thoroughly mixed before use. This is best achieved by slow, gentle hand stirring with a clean, burr-free spatula (flexible plastic or stainless steel) for 1-2 minutes. Care must be taken to avoid air-bubble entrapment. Printing should be carried out in a clean, well-ventilated area.

Note: optimum printing characteristics of DuPont 9615 are generally achieved in the temperature range 20°C-23°C. It is therefore important that the material, in its container, is at this temperature prior to commencement of printing.

Screen printed with a 200 mesh stainless steel screen to obtain a fired thickness of 12µm. Two layers separately fired are recommended for maximum hermetic.

Composition Properties

Test	Properties
Viscosity (Pa.s) (Brookfield HBF, spindle#5, 10 rpm, 25°C)	170 - 230
Coverage (cm ² /gm)	83
Thinner	DuPont 9180R

This table shows anticipated typical physical properties for DuPont 9615R based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Drying

Allow prints to level for 5-10 minutes at room temperature in a clean, draught-free environment, followed by drying for 10-15 minutes at 150°C in a well ventilated oven or conveyor dryer.

Firing

Fire in a well ventilated belt or conveyor furnace in air with a 30-60 minute cycle with a peak of 850°C held for 10 minutes. See Figure 1 & Figure 2. Care must be taken to ensure that any gases/vapors from other chemicals/materials (e.g. halogenated solvents) do not enter the furnace muffle. It is also essential that the air supply to the furnace is clean, dry and free of contaminants. Air flows and extraction rates should be optimized to ensure that oxidizing conditions exist within the muffle, and that no furnace exhaust gases enter the room.

General

Yield and performance will depend to a large degree on the care exercised during processing, particularly in screen printing. Scrupulous care should be taken to keep the encapsulant composition, printing screens and other tools free of metal contaminations. Dust, lint and other particulate matter may also contribute to poor yields.

Figure 1 - 30 minutes Profile





Figure 2 - 60 minutes Profile (Typical 850°C 60 minute Profile)



Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).



Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates (“DuPont”). NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 (“Medical Applications Policy”) and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user’s consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data’s accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user’s responsibility to satisfy itself that the product is suitable for the user’s intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



The miracles of science™

For more information on DuPont 9615R or other DuPont Microcircuit Materials products, please contact your local representative:

Americas

DuPont Microcircuit Materials
14 T.W. Alexander Drive
Research Triangle Park, NC 27709
Tel.: 800-284-3382

Europe

Du Pont (U.K.) Limited
Coldharbour Lane
Bristol BS16 1QD
U.K.
Tel.: 44-117-931-3191

Asia

DuPont Kabushiki Kaisha
Sanno Park Tower, 11-1
Nagata-cho 2-chome
Chiyoda-ku, Tokyo 100-611
Japan
Tel.: 81-3-5521-8650

DuPont Taiwan Ltd
45, Hsing-Pont Road,
Taoyuan, Taiwan 330
Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,
Pudong New District, Shanghai 201203, China
Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.
3~5th Floor, Asia tower #726,
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens,
Sector-25A, DLF City, Phase-III,
Gurgaon 122 002 Haryana, India
Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFront Tower One,
Singapore 098633
Tel.: 65-6586-3022

<http://mcm.dupont.com>