DuPont 5436D RESISTORS ENCAPSULANT

Technical Data Sheet

Product Description

DuPont 5436D is a screen printable low temperature firing, protective glass encapsulant for chip resistors.

Product Benefits

- Acid resistant, withstands acidic nickel plating conditions
- Low firing temperatures: 600 to 620 C at 30 • minutes profile
- Excellent printability •
- Black color, opaque appearance •
- Cadmium-free*

*Cadmium "free" as used herein means that cadmium is not an intentional ingredient and is not intentionally added to the referenced product.

Processing Printing

Print a dried print thickness of 18 to 20 µm with a 325 mesh stainless steel screen to give a minimum fired thickness of 10 µm.

Drying

Prints should be allowed to level at room temperature for 5 - 10 minutes and then dried 10 minutes at 150°C.

Firina

Fire to peak temperature of 600° - 620°C for 5 -10 minutes at peak with total firing cycle of 30 minutes. Allow adequate time (5 - 10 minutes) during heating cycle to avoid entrapment of organics in the fired film.

Composition Properties

Test	Properties
Viscosity (Pa-s) [Brookfield HBT, UC&S, 10 rpm, 25+/- 1 C]	100-170
Thinner	DuPont 8250

This table shows anticipated typical physical properties for DuPont 5436D based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature Shelf life of material in unopened (<25°C). containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont[™], The miracles of science[™], Green Tape[™] and all products or words denoted with ® or [™] are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates ("DuPont"). NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H -50103-2 ("Medical Applications Policy") and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user's consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data's accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user's responsibility to satisfy itself that the product is suitable for the user's intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for the particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.

UPOND The miracles of science[™] For more information on DuPont 5436D or other DuPont Microcircuit

Materials products, please contact your local representative:

Americas

DuPont Microcircuit Materials

14 T.W. Alexander Drive

Research Triangle Park, NC 27709

Tel.: 800-284-3382

Europe

Du Pont (U.K.) Limited

Coldharbour Lane

Bristol BS16 1QD

U.K.

Tel.: 44-117-931-3191

<u>Asia</u>

DuPont Kabushiki Kaisha

Sanno Park Tower, 11-1

Nagata-cho 2-chome

Chiyoda-ku, Tokyo 100-611

Japan

Tel.: 81-3-5521-8650

DuPont Taiwan Ltd 45, Hsing-Pont Road, Taoyuan, Taiwan 330 Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park, Pudong New District, Shanghai 201203, China Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc. 3~5th Floor, Asia tower #726, Yeoksam-dong, Gangnam-gu Seoul 135-719, Korea Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited 7th Floor, Tower C, DLF Cyber Greens, Sector-25A, DLF City, Phase-III, Gurgaon 122 002 Haryana, India Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd 1 HarbourFront Place, #11-01 HarbourFrong Tower One, Singapore 098633 Tel.: 65-6586-3022

http://mcm.dupont.com