

DUPONT™ KA701

POLYIMIDE ENCAPSULANT/DIELECTRIC

PRODUCT DESCRIPTION

DuPont[™] KA701 is a screen printable polyimide encapsulant. This composition is particularly suited for applications where high operating temperatures are required.

PRODUCT BENEFITS

- Good encapsulant or dielectric
- Good thermal/chemical stability
- Excellent adhesion to a variety of substrates

PROCESSING

Substrates

• Kapton® FPC, Kapton® RS, FR-4, Aluminum, Alumina, glass

Screen Printing Equipment

- Automatic reel-to-reel
- Semi-automatic flat-bed

Screens

• 200-mesh stainless steel (0.5 - 1.0 mil)

A minimum of 2 prints is strongly recommended.

Drying

Box oven: 130-200°C for 30 minutes Reel-to-reel: 130-200°C for 2-4 minutes

*Equipment dependent

Clean-up Solvent

Butyl carbitol acetate

Table 1-Typical Composition Properties

Test	Properties
Solids (%) @ 150°C	38.0 – 42.0
Viscosity (PaS) [Brookfield 0.5 x RVT, #14 Spindle, 10 RPM, 25°C]	50 – 150
Coverage (cm²/g) @8µm	320
Thinner	DuPont™ 8218
Color	White

Table 2-Typical Physical Properties

Test	Properties
Insulation Resistance (GΩ/sq/mil)	~10
Adhesion Crosshatch [ASTM D2259-78] Dielectric to PolyesterScotch Tape #600 (B) Conductor to Dielectric	No transfer*
Flexibility (180°C crease over KA801)	No opens
Breakdown Voltage (kV/mil DC)	>1
Dielectric Constant (@1kHz)	<5

Tables 1 & 2 show anticipated typical physical properties for DuPont™ KA701 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

STORAGE AND SHELF LIFE

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

SAFETY AND HANDLING

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

WARNING

Do not process/use this material above 300°C due to the risk for potential release of hydrogen fluoride.

^{*}Parts for adhesion dried at 200°C/30min on plasma treated Kapton®.



DUPONT™ KA701 POLYIMIDE ENCAPSULANT/DIELECTRIC

FOR MORE INFORMATION ON DUPONT™ KA701 OR OTHER DUPONT MICROCIRCUIT MATERIALS PRODUCTS, PLEASE CONTACT YOUR LOCAL REPRESENTATIVE:

Americas

DuPont Microcircuit Materials 14 TW Alexander Drive Research Triangle Park, NC 27709 USA

Tel +1 800 284 3382 (calls within USA) Tel +1 919 248 5188 (calls outside USA)

Europe, Middle East & Africa

Du Pont (UK) Ltd Coldharbour Lane Bristol BS16 1QD UK Tel +44 117 931 3191

Asia

Du Pont Kubushiki Kaisha MCM Technical Lab DuPont Electronics Center KSP R&D B213, 2-1, Sakado 3-chome, Takatsu-ku, Kawasaki-shi, Kanagawa, 213-0012 Japan Tel +81 44 820 7575

DuPont Taiwan Ltd 45, Hsing-Pont Road Taoyuan, 330 Taiwan Tel +886 3 377 3616

DuPont China Holding Company Ltd Bldg. 11, 399 Keyuan Road Zhangjiang Hi-Tech Park Pudong New District Shanghai 201203 Tel +86 21 3862 2888 DuPont Korea Inc. 3-5th Floor, Asia tower #726 Yeoksam-dong, Gangnam-gu Seoul 135-719, Korea Tel +82 2 2222 5275

E.I. DuPont India Private Limited 7th Floor, Tower C, DLF Cyber Greens Sector-25A, DLF City, Phase-III Gurgaon 122 002 Haryana, India Tel +91 124 409 1818

Du Pont Company (Singapore) Pte Ltd 1 HarbourFront Place, #11-01 HarbourFront Tower One Singapore 098633 Tel +65 6586 3022

mcm.dupont.com

Copyright © 2016 DuPont. All rights reserved. The DuPont Oval Logo, DuPontTM, and all DuPont products denoted with @ or TM are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in end-use conditions, DuPont makes no warranties, and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5. K-29319 (6/16)