

# DuPont 5739

GOLD/PLATINUM COFIREABLE SOLDERABLE CONDUCTOR

## Technical Data Sheet

### Product Description

DuPont 5739 is an external gold/platinum conductor compatible with DuPont™ GreenTape™ 951 low temperature co-fired ceramic system. DuPont 5739 is ideally suited for solder applications.

### Product Benefits

When used with GreenTape™ 951 and compatible via fill pastes, DuPont 5739 offers the following benefits:

- High reliability
- Superior solder acceptance
- Cofire processing

### Processing

#### Design

For detailed recommendations on use of GreenTape™ 951 and conductors such as DuPont 5739, see the GreenTape™ 951 Design Guide and GreenTape™ 951 Product Data Sheet. For compatible thick film compositions and their recommended use see the GreenTape™ 951 Product Selector Guide.

#### Thinning

Thinning thick film compositions is not recommended as material is supplied formulated for optimal performance. Improper thinning may affect printing characteristics. Thinner may be added to replenish solvent lost during normal usage but care should be taken to not over-thin.

#### Drying

Dry in air in a well-ventilated oven or conveyor dryer for 5 minutes at 120°C. Do not over-dry.

### Composition Properties

Test	Properties
Clean-Up Solvent	1-Propoxy-2-Propanol
Thinner	DuPont 8250
Coverage <sup>1</sup> , cm <sup>2</sup> /g	80-90
Viscosity (Pa.s) (Brookfield HBT, UC&SP, 10 rpm, 25°C)	175-300
Typical Properties	
Dried Line Resolution (µm ) (lines/spaces)	125/125
Dried Thickness (µm)	19-25
Fired Thickness (µm )	10-15
Fired Resistivity <sup>2</sup> (mΩ/sq)	< 35
Solder Acceptance (%)	> 99
Adhesion Strength <sup>3</sup> Initial (N) Aged (N)	>25 >20
<small><sup>1</sup>Calculated at a wet thickness of 25 µm <sup>2</sup>At 12 µm fired film thickness <sup>3</sup>Aging consists of 240 hours at 150°C</small>	

Table 1 & 2 show anticipated typical physical properties for DuPont 5739 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

## Printing

The composition should be thoroughly mixed before use. This is best achieved by slow, gentle, hand stirring with a clean burr-free spatula (flexible plastic or stainless steel) for 1-2 minutes. Care must be taken to avoid air entrapment.

Printing should be performed in a clean and well-ventilated area. Optimum printing characteristics are generally achieved in the room temperature range of 20-23°C. Viscosity, and therefore printability, of thick film compositions can be affected by ambient temperatures.

Print DuPont 5739 directly onto unfired GreenTape™ 951 using thick film printing methods and a vacuum stone or other support structure that uniformly distributes vacuum. A 325 mesh stainless steel screen with 12 µm emulsion is standard.

## Lamination and Firing

Laminate multiple sheets of GreenTape™ 951 onto which DuPont 5739 has been printed according to processing parameters detailed in the GreenTape™ 951 Design Guide and on the GreenTape™ 951 Product Data Sheet. Consult these documents as well for details of the recommended GreenTape™ 951 firing profile for belt or box air furnaces.

DuPont 5739 performs well with up to two refires under optimal conditions. It is important to ensure adequate air-flow to the part during both firing and refiring. DuPont 5739 is not recommended for use buried or in completely enclosed cavities.

## Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

## Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).



*The miracles of science™*

For more information on DuPont 5739 or other DuPont Microcircuit Materials products, please contact your local representative:

### Americas

DuPont Microcircuit Materials

14 T.W. Alexander Drive

Research Triangle Park, NC 27709

Tel.: 800-284-3382

### Europe

Du Pont (U.K.) Limited

Coldharbour Lane

Bristol BS16 1QD

U.K.

Tel.: 44-117-931-3191

### Asia

DuPont Kabushiki Kaisha

DuPont Electronic Center

KSP R&D B213, 2-1, Sakado 3-chome, Takatsu-ku,

Kawasaki-shi, Kanagawa, 213-0012, Japan

Tel: +81-44-820-7575

DuPont Taiwan Ltd

45, Hsing-Pont Road,

Taoyuan, Taiwan 330

Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd

Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,

Pudong New District, Shanghai 201203, China

Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.

3~5th Floor, Asia tower #726,

Yeoksam-dong, Gangnam-gu

Seoul 135-719, Korea

Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited

7th Floor, Tower C, DLF Cyber Greens,

Sector-25A, DLF City, Phase-III,

Gurgaon 122 002 Haryana, India

Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd

1 HarbourFront Place, #11-01

HarbourFront Tower One,

Singapore 098633

Tel.: 65-6586-3022

<http://www.mcm.dupont.com>

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates (“DuPont”).

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 (“Medical Applications Policy”) and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user’s consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data’s accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user’s responsibility to satisfy itself that the product is suitable for the user’s intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



*The miracles of science™*

MCM5739 (8/2013)