

DuPont™ 7775

Silver Conductive Polymer Paste

Product Description

DuPont™ 7775 is a silver conductive paste developed primarily as a tantalum capacitor coating. This composition utilizes a thermoplastic resin and can be used in other dipping applications. DuPont™ 7775 provides low ESR for the conductive polymer tantalum capacitors with small case sizes recommended.

Product Benefits

- Excellent dipping conformation with one shot dipping
- Uniform thin thickness at chip corners
- Good paste stability without separation after solvent dilution
- Low cure temperature.

Processing

Thinning

Use the DuPont recommended thinner for the adjustments to viscosity or to replace evaporation losses. The use of non-recommended thinner may affect the rheological behavior of the material and its printing characteristics. Recommended thinning ration is 20-30 out of 100.

Typical Curing Condition

Allow prints to level at room temperature, then dry in a well ventilated oven at 160°C for 60 minutes or conveyor dryer/IR dryer with other condition less than 200°C. Drying with high temperature oven/dryer may affect binder's quality in the product.

Typical & Composition Properties

Test	Properties
Resistivity ($\mu\Omega\cdot\text{cm}$)	0 - 20
Viscosity (Pa.s) [RVT UC&S 10rpm]	5 - 30
Solid (%) [750°C Wt.]	56 - 59
Thinner	DuPont™ 8225

This table shows anticipated typical physical properties for DuPont™ 7775 based on specific controlled experiments in our labs and are not intended to represent to product specifications, details of which are available upon request.

Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is three months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For Safety and Handling information pertaining to this product, read the material Safety Data Sheet (SDS).